

Velvet Satin

Acrylic copolymer-based washable paint



Technical Data Sheet N°926



Satin Velouté



USAGE

INTERIOR

For vertical surfaces. For use in all indoor rooms.

Base surfaces: For application to all ordinary and correctly-primed structural surfaces. On iron, a coat of an appropriate corrosion-inhibiting primer should be applied beforehand.

KEY QUALITIES

Water-dilutable acrylic copolymer-based paint, with a fine satin finish, soft and smooth to the touch. Washable low-gloss finish. Class 1 wet abrasion resistance⁽²⁾: exceptionally easy maintenance. Application by either roller or brush makes this paint ideal for walls and framework structures. Non-yellowing, and with no residual tack.

DEPLOYMENT

PREPARATION OF BASE SURFACES

Base surfaces must be entirely free of dust, sound, dry, of uniform quality and thoroughly cleaned. Apply a coat of primer and/or undercoat which is appropriate to the base surface and the shade. For low-opacifying shades, it is highly recommended to use the Bonding Undercoat (Dark) in the finishing shade (consult the relevant shade card in-store).

EQUIPMENT FOR APPLICATION

For application using a special acrylic brush or microstar 3/8" (10 mm) roller. For a smooth finish, use a microstar 3/8" (10 mm) roller, then smooth with a spalter brush in a uniform manner.

TYPES OF BASE SURFACES	PREPARATION
Plasterboard panels, old and well-adhered paintwork, etc. (low-porosity base surfaces).	Sand down lightly and remove dust. Wash down and rinse if necessary. Prime with General-purpose Primer or Bonding Undercoat.
Brickwork, plaster, etc. (porous, powdery or chalky base surfaces).	Prime with Universal Primer (then with a coloured undercoat, if necessary).

APPLICATION

Once the undercoat is completely dry, apply two coats of **VELVET SATIN** using a brush or roller, diluting with approximately 5% of water.

In an airless sprayer or conventional spray gun, depending upon the device used, the varnish may require dilution with 10 – 20% of water. A number of tests should be executed on card or on a concealed area, in order to arrive at the optimum dilution.

Advice: We would recommend the testing of the dilution factor on a small surface, in order to determine the appropriate percentage (the paint must not resist, but must slide easily onto the base surface to be covered). Optimum dilution of the paint permits correct application (a good finish) and easy application.

GENERAL CHARACTERISTICS

Appearance	Velvet satin finish
Gloss rating	8 - 10 UB at 60°
Coverage	590 sq.Ft/Gal; 156 sq.Ft /Liter per coat, according to the device and dilution selected.
Drying	30 minutes (touch dry).
Ready for recoating	Velvet Satin Finish: Approx. 4 hours (according to temperature and atmospheric humidity).
Dry extract	56% by weight, 41% by volume.
Cleaning of tools	With water.
Density	1.33
Packaging	1 Liter, 1 Gallon, 10 Liters
Storage	1 year in unopened original packaging. Protect from frost.
Colour matching	All Ressource shades (available in 5 base versions).

PRECAUTIONS

For application between 46°F (8°C) and 95°F (35 °C).
Do not apply where the relative humidity exceeds 70%.

For low-opacifying shades, it is highly recommended to use the Bonding Undercoat (Dark) in the finishing colour (consult the relevant shade card in-store).

REGULATORY CHARACTERISTICS

VOC (1)	This product contains 0g/l VOC in use.
SAFETY	See the Safety Data Sheet, Compliant with legislation in force.

(1) Volatile Organic Compounds: Directive 2004/42/EC

(2) In accordance with standards ISO 11998 and EN 13300, the paint film withstands cleaning with a soft sponge and a non-corrosive household product. However, attention must be paid to the risk of buffing, particularly on uniform shades.

* Information on the level of emissions of volatile substances in an interior atmosphere, associated with the risk of toxicity by inhalation, on a scale of class ratings from A+ (very low emissions) to C (high emissions).

Velvet Satin

Technical Data Sheet N° 926, 7th April 2018 edition. This technical data sheet supersedes and replaces previous editions pertaining to the same product. In the light of continuous technical development, it is the responsibility of clients to confirm, prior to application and by consultation with our services, that the present technical data sheet has not been modified by a more recent edition.

Document available for consultation on our website at www.ressource-peintures.com

RESSOURCE