

EXTERIOR WOOD PRIMER

Filling microporous wood primer.

RECOMMENDED USE

Outdoors.

For vertical surfaces and ceilings, in all climatic and atmospheric conditions.

Substrates: Wooden shutters, woodwork, previously painted wood.

BENEFITS

A microporous wood primer with a low solvent content (high solid content). Excellent filling properties, even on edges. Allows humidity to evaporate without blistering or flaking. Adheres to most types of wood available.

SURFACE PREPARATION

The surface must be perfectly dusted, dry, sound and very clean.

Bare wood: Clean the surface using the appropriate mechanical tools or chemicals. Check the wood's moisture content: 18% max. Wipe the surface clean.

Exotic wood: Remove any grease from the surface and apply the Exterior Woodworks Primer.

New tannic wood: Clean the surface using the appropriate mechanical tools or chemicals.

Softwood: Scrape and clean with aromatic solvent.

Maintenance work: Clean the surface using the appropriate mechanical tools or chemicals.

Renovation work: If the surface is damaged in any way or if other incompatible types of paint have been used previously, strip the wood.

Application tools: Apply with a brush or a 5 or 10mm microfiber roller.

APPLICATION

Apply one coat of Exterior Wood Primer, pure or diluted with 5 to 10% white spirit. Then, apply 2 coats of Exterior Wood Velvet Matte or Semi Gloss.

GENERAL INFORMATION

Appearance: Satin.

Coverage: 10-12m²/L depending on the porosity of the surface.

Drying time: 4h (dry to the touch).

Second coat: 24h depending on the temperature and air humidity: < 80% outdoors.

Solid content: 82% in weight, 62% in volume.

Density: 1.47g/cm³.

How to clean your equipment: White Spirit.

Packaging: 0.5L and 2.5L.

Storage: 1 year in its original unopened packaging. Keep away from frost.

HANDLE WITH CARE

Use in temperatures between +5°C and +30°C. Do not use when relative humidity is more than 80%. Never paint in atmospheric conditions that may cause condensation or on frozen or overheated surfaces, or in conditions that would cause the paint to dry abnormally quickly (wind, sun, etc.). Not suitable for cracked or damaged wood, for wood types that are unrecognized for exterior use, in the event of resin exudation or excessive moisture content.

REGULATORY INFORMATION

AFNOR Classification: Family I - Classe 4a.

VOC⁽¹⁾: The 2010 EU limit value for this product (cat A/h) is 750g/L. This product contains maximum 400g/L VOC.

Safety: Refer to the safety Data Sheet (SDS). Complies with current legislation.

⁽¹⁾ Volatile Organic Compounds: Directive 2004/42/EC

* Information on the emission of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on the class scale from A+ (very low emissions) to C (high emissions).