

## SATIN SOLVENT PAINT

Satin glycerophthalic lacquer with a velvet finish.



### RECOMMENDED USE

#### Indoors and outdoors.

On sheltered vertical surfaces. In all indoor rooms.

Substrates: All standard building materials that have been properly primed. If you are painting on iron, apply a rustproof primer first.

### BENEFITS

- Satin smooth glycerophthalic resin-based lacquer.
- High filling power and opacity.
- Excellent drying time and easy to apply.
- Class 1<sup>(2)</sup> wet abrasion resistance (after 28 days of drying): very low maintenance.

### SURFACE PREPARATION

The surface must be perfectly cleaned, dusted and dry. Apply the appropriate primer and/or undercoat for the substrate.

**Slightly porous surfaces, previously painted surfaces in good condition:** For previously painted surfaces, sand and dust. Wash and rinse if necessary. On slightly porous surfaces, apply our Undercoat for Regular Work, or Undercoat for Light or Dark Colours.

**Porous, powdery or chalky surfaces:** Apply our Solvent-based Primer diluted with 5-10% White Spirit.

**Application tools:** Apply using a brush, a 5 or 10mm lacquer roller, an airless or pneumatic sprayer.

### APPLICATION

Once the primer is completely dry, apply two coats of Satin Solvent Paint using a brush or a roller.

### GENERAL INFORMATION

**Finish:** Satin Velvet.

**Gloss:** 15 to 25GU at 60° and 50 to 60GU at 85° (leave 7 days for maximum gloss).

**Coverage:** 10-12m<sup>2</sup>/L per coat depending on your choice of dilution and equipment.

**Drying time:** 6h (dry to the touch).

**Second coat:** Approx. 24h (depending on the temperature and air humidity).

**Solid content:** 78% in weight, 58% in volume.

**Density:** 1.46g/cm<sup>3</sup>.

**How to clean your equipment:** White Spirit.

**Packaging:** 1L, 2.5L and 5L.

**Storage:** 1 year in its original unopened packaging. Keep away from frost.

**Tinting:** All Ressource colours (available in 5 bases).

**HANDLE WITH CARE**

Use in temperatures between +5°C and +30°C. Do not use when relative humidity is more than 75%.

**REGULATORY  
INFORMATION**

**AFNOR Classification:** Family I - Class 4a.

**VOC<sup>(1)</sup>:** The 2010 EU limit value for this product (cat A/d) is 300g/L.  
This product contains maximum 300g/L VOC.

**Safety:** Refer to the safety Data Sheet (SDS). Complies with current legislation.

<sup>(1)</sup> Volatile Organic Compounds: Directive 2004/42/EC.

<sup>(2)</sup> According to ISO 11998 and EN 13300, the paint film is resistant to cleaning with a sponge, using gentle household products. Take care as washing may leave a sheen on some strong colours.

\* Information on the emission of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on the class scale from A+ (very low emissions) to C (high emissions).