

EXTERIOR WOOD VELVET MATTE

Microporous glycerophthalic lacquer paint with high solid content

Matte  — Gloss
Recommended use: **woodwork and exterior wood**
Easy to apply 

RECOMMENDED USE

Outdoors.

For vertical surfaces, in all climatic and atmospheric conditions.

Substrates: Wooden shutters, woodwork, old painted wood. If you are painting iron, apply a Rustproof Primer first.

BENEFITS

- Microporous paint.
- Water vapour resistant, allows the substrate to breathe.
- Waterproof, protects the substrate.
- Very supple, follows the dimensional variations of the wood.
- Excellent filling power, long-lasting.

SURFACE PREPARATION

The surface must be perfectly dusted, dry, sound and very clean.

Application tools: Apply using a brush, a 5mm or 10mm microfiber roller.

APPLICATION

Ready to use.

Bare wood: Check the wood's moisture content: 18% max. Wipe the surface clean. Apply 1 coat of Exterior Wood Primer and 2 coats of Exterior Wood Velvet Matte.

Exotic wood: Remove any grease from the surface and apply the Exterior Wood Primer and 2 coats of Exterior Wood Velvet Matte.

Maintenance work: Clean the surface using the appropriate mechanical tools or chemicals. Apply 2 coats of Exterior Wood Velvet Matte.

Renovation work: If the surface is damaged in any way or if other incompatible types of paint have been used previously, strip the wood bare and apply 1 coat of Exterior Wood Primer and 2 coats of Exterior Wood Velvet Matte.

GENERAL INFORMATION

Appearance: Velvet Matte.

Gloss: 10 to 15GU at 60° and 40 to 60GU at 85° after drying for 7 days.

Coverage: 10-12m²/L per coat.

Drying time: 4-5h (dry to the touch).

Second coat: Approx. 24h depending on temperature and air humidity: < 80% outdoors.

Solid content: 80% in weight, 60% in volume.

Density: 1.42g/cm³.

How to clean your equipment: White Spirit.

Packaging: 0.5L, 2.5L and 5L.

GENERAL INFORMATION

Storage: 1 year in its original unopened packaging. Keep away from frost.

HANDLE WITH CARE

Use in temperatures between +5°C and + 30°C. Do not use when relative humidity reaches more than 80%. In places that are exposed to sunlight, do not use dark shades whatever the surface (sun absorption coefficient > 0.7). Never paint in atmospheric conditions that may cause condensation or on frozen or overheated surfaces, or in conditions that would cause the paint to dry abnormally quickly (wind, sun, etc.). Not suitable for cracked or damaged wood, for wood types that are unrecognized for exterior use, in the event of resin exudation or excessive moisture content.

REGULATORY INFORMATION

AFNOR Classification: Family I - Class 4a.

VOC⁽¹⁾: The 2010 EU limit value for this product (cat A/d) is 300g/L. This product contains maximum 300g/L VOC.

Safety: Refer to the safety Data Sheet (SDS). Complies with current legislation.

⁽¹⁾ Volatile Organic Compounds: Directive 2004/42/EC

* Information on the emission of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on the class scale from A+ (very low emissions) to C (high emissions).