

SATIN SOLVENT

Satin glycerophthalic lacquer with a velvet finish.



RECOMMENDED USE

Indoors and outdoors.

On interior woodwork and exterior sheltered surfaces.

Substrates: All standard building materials that have been properly primed. If you are painting on iron, apply a Rustproof Primer first.

BENEFITS

- Satin smooth glycerophthalic resin-based lacquer.
- High filling power and opacity.
- Excellent drying time and easy to apply.
- Class 1⁽²⁾ wet abrasion resistance (after 28 days of drying): very low maintenance.

SURFACE PREPARATION

The surface must be perfectly cleaned, dusted and dry. Apply the appropriate primer and/or undercoat for the substrate.

Slightly porous surfaces, previously painted surfaces in good condition: For previously painted surfaces, sand and dust. Wash and rinse if necessary. On slightly porous surfaces, apply our Undercoat for Regular Work, or Undercoat for Light or Dark Colors.

Porous, powdery or chalky surfaces: Apply our Solvent-based Primer diluted with 5-10% White Spirit.

Application tools: Apply using a brush, a 5 or 10mm lacquer roller, an airless or pneumatic sprayer.

APPLICATION

Once the primer is completely dry, apply two coats of Satin Solvent using a brush or a roller.

GENERAL INFORMATION

Finish: Satin Velvet.

Gloss: 30 to 40GU at 60° (leave 7 days for maximum gloss).

Coverage: 10-12m²/L per coat depending on your choice of dilution and equipment.

Drying time: 6h (dry to the touch).

Second coat: Approx. 24h (depending on the temperature and air humidity).

Solid content: 78% in weight, 58% in volume.

Density: 1.46g/cm³.

How to clean your equipment: White Spirit.

Packaging: 1L, 2.5L and 5L.

Storage: 1 year in its original unopened packaging. Keep away from frost.

Tinting: All Ressource colours (available in 5 bases).

HANDLE WITH CARE

Use in temperatures between +5°C and +30°C. Do not use when relative humidity is more than 75%.

**REGULATORY
INFORMATION**

AFNOR Classification: Family I - Class 4a.

VOC⁽¹⁾: The 2010 EU limit value for this product (cat A/d) is 300g/L.
This product contains maximum 300g/L VOC.

Safety: Refer to the safety Data Sheet (SDS). Complies with current legislation.

⁽¹⁾ Volatile Organic Compounds: Directive 2004/42/EC.

⁽²⁾ According to ISO 11998 and EN 13300, the paint film is resistant to cleaning with a sponge, using gentle household products. Take care as washing may leave a sheen on some strong colours.

* Information on the emission of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on the class scale from A+ (very low emissions) to C (high emissions).