

EMPREINTE

Plaster coating with crushed crisscrossed effects.

RECOMMENDED USE

Indoors.

For vertical surfaces, in all dry rooms.

Substrates: On all standard building materials that have been properly primed.

BENEFITS

Structured plaster leaving a print effect on the wall.

SURFACE PREPARATION

The surface must be perfectly cleaned, dusted and dry. Wash any remaining old paint, then sand and dust again, if necessary. On powdery or porous substrates, first apply a coat of Universal Primer.

Application tools: Apply the Rough Primer using a 1/2" (12mm) microfibre roller.

Apply the Mineral Plaster Undercoat and Empreinte using a stainless steel smoothing trowel and effect comb.

Apply the Metallic Paint and the Walls and Furniture Velatura using a 1/4" (5mm) mini roller.

APPLICATION

Generously cover the surface with a Rough Primer but avoid any build-up of thickness to ensure the plaster adheres to the surface.

Mineral Plaster Undercoat: After the Rough Primer has dried (approx. 12h), apply the undercoat using a smoothing trowel and cover the surface in fine layers making rounded continuous movements. Start at the top of the wall and make your way down without exerting too much pressure. Adjust the thickness to the Rough Primer. Work on surfaces of approx. 20 to 40sq.Ft (2 to 4m²) and leave the walls to dry for 12h when your work is complete.

Empreinte: Apply generously using a smoothing trowel working on areas of 16.5sq.Ft (1.5m²) for an even thickness. Using the effect comb, make horizontal and vertical strokes exerting very light pressure.

Leave to dry for approx. 2h until the plaster is soft but dry to the touch. Press down on the surplus of product with the stainless steel mini trowel creating diagonals in both directions to obtain a cross shape. Do this randomly all over the surface to make the structure appear.

Finition: Metallic effect : Once the plaster is dry (12h minimum), apply one coat of Metallic Paint using a 1/4" (5mm) microfiber mini roller drawing diagonals in both directions to obtain a cross shape but without pressing down so as to apply the product only to the parts in relief.

Shimmering effect : Once the plaster is dry, apply one coat of Walls and Furniture Velatura (patine C) using a 1/4" (5mm) microfiber mini roller drawing diagonals in both directions to obtain a cross shape but without pressing down so as to apply the product only to the parts in relief.

GENERAL INFORMATION

Appearance: Metallic or shimmering.

Coverage: Mineral Plaster Undercoat: 109sq.Ft/Gal; 290sq.Ft/10L (2.7m²/L approx.).

Empreinte: Approx. 90sq.Ft/Gal; 240sq.Ft/10L (2.2m²/L approx.).

Walls and Furniture Velatura: Approx. 1020sq.Ft/Gal; 269sq.Ft/L (25m².L approx.).

Metallic Paint: 710sq.Ft/Gal; 94sq.Ft/Half Liter (17m²/L approx.).

GENERAL INFORMATION

Drying time: Mineral Plaster Undercoat: 30mins (dry to the touch).

Empreinte: Approx. 12h.

Walls and Furniture Velatura: Approx. 4h.

Metallic Paint: Approx. 4h.

Second coat: Mineral Plaster Undercoat: 12h.

Empreinte: Approx. 24h.

Solid content: Mineral Plaster Undercoat: 76% in weight, 55% in volume.

Empreinte: 75% in weight, 55% in volume.

Walls and Furniture Velatura: 3.5% in weight, 3.3% in volume.

Metallic Paint: Approx. 30% in weight, 26% in volume.

Density: Mineral Plaster Undercoat: 1,36g/cm³.

Empreinte: 1,80g/cm³.

Walls and Furniture Velatura: 1g/cm³.

Metallic Paint: Approx. 1.06g/cm³.

How to clean your equipment: Water.

Packaging: Mineral Plaster Undercoat: 1Gal and 10L.

Empreinte: 1Gal and 10L.

Walls and Furniture Velatura: 1L.

Metallic Paint: 0.5L and 1Gal.

Storage: 1 year in its original unopened packaging. Keep away from frost.

HANDLE WITH CARE

Use in temperatures between 41°F (5°C) and 86°F (30°C). Do not use when relative humidity reaches more than 75%. This plaster contains slaked lime so it is essential you protect your eyes and wear gloves while applying.

REGULATORY INFORMATION

VOC regulatory⁽¹⁾: This product contains 50g/L VOC in use.

Safety: Refer to the safety Data Sheet (SDS) for health and safety information.

⁽¹⁾ Volatile Organic Compounds: Federal Regulations 40CFR59.